

10-16-00

A

10/13/00

JCS55 B.S. PTO

UTILITY PATENT APPLICATION TRANSMITTAL

(Only for new nonprovisional applications under 37 CFR § 1.53(b))

Attorney Docket No. 2000U026.US

Inventors Sun-Chueh KAO

Title A METHOD FOR PREPARING A CATALYST SYSTEM AND ITS USE IN A POLYMERIZATION PROCESS

Express Mail Label No. EL715559489US

APPLICATION ELEMENTS

ADDRESS TO:

Assistant Commissioner for Patents
Box Patent Application
Washington, D.C. 20231

1. ☒ Fee Transmittal Form (e.g., PTO/SB/17)
(Submit an original, and a duplicate for fee processing)
2. ☒ Specification Total Pages 29
(preferred arrangement set forth below)
 - Descriptive Title of the Invention
 - Cross References to Related Applications (if any)
 - Background of the Invention
 - Brief Summary of the Invention
 - Brief Description of the Drawings (if filed)
 - Detailed Description
 - Claim(s)
 - Abstract of the Disclosure
3. ☐ Drawing(s) (35 U.S.C. 113) Total Sheets -0-
4. ☒ Oath or Declaration Total Pages -2-
(unsigned)
 - a. ☐ Newly executed (original or copy)
 - b. ☐ Copy from a prior application (37 C.F.R. § 1.63(d)
(for continuation/division with Box 15 completed)
[Note Box 5 below]
 - i. ☐ DELETION OF INVENTOR(S)
Signed statement attached deleting
inventor(s) named in the prior application,
see 37 C.F.R. §§ 1.63(d)(2) and 1.33(b).

5. ☐ Incorporation By Reference (useable if Box 4B is checked)
The entire disclosure of the prior application, from which a copy of the oath is supplied under Box 4b, is considered to be part of the disclosure of the application and is hereby incorporated by reference therein
6. ☐ Microfiche Computer Program (Appendix)

ACCOMPANYING APPLICATION PARTS

7. ☐ Assignment Papers (cover sheet & document(s))
8. ☐ 37 C.F.R. § 3.73(b) Statement ☐ Power of Attorney,
(when there is an assignee)
9. ☐ English Translation Document (if applicable)
10. ☒ Information Disclosure Statement (IDS)/PTO-1449
☒ Copies of IDS Citations
11. ☐ Preliminary Amendment
12. ☒ Return Receipt Postcard (MPEP 503)
(Should be specifically itemized)
13. ☐ Certified Copy of Priority Document(s)
(if foreign priority is claimed)
14. ☐ Other:

15. If a CONTINUING APPLICATION, check appropriate box, and supply the requisite information below and in a preliminary amendment.

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP)

of prior applications No: _____, from which priority is claimed under 35 U.S.C. § 120

Prior application information: Examiner _____ Group Art Unit


16. If a NONPROVISIONAL APPLICATION based upon a foreign or U.S. provisional application, priority is claimed from applications

No. _____, country _____, filed on _____.

17. CORRESPONDENCE ADDRESS

☐ Customer Number or Bar Code Labelor ☒ Correspondence address below

(Insert Customer No. or Attach bar code label here)

Name	Univation Technologies, LLC				
Address	5555 San Felipe, Suite 1950				
City	Houston	State	Texas	Zip Code	77056
Country	U.S.A.		Telephone	(713) 892-3668	Fax (713) 892-3687
Name (print/type)	Jaimes Sher		Registration No. (Attorney/Agent)	34,726	
Signature			Date	October 13, 2000	

 JCS41 U.S. PTO
09/687734
10/13/00

TRANSMITTAL FORM

(to be used for all correspondence after initial filing)


TRANSMITTAL FORM (to be used for all correspondence after initial filing)		Application Number	Unknown
		Filing Date	October 13, 2000
		First Named Inventor	KAO, Sun-Chueh
		Group Art Unit	Unassigned
		Examiner Name	Unassigned
Total Number of Pages in This Submission	4 (+references)	Attorney Docket Number	2000U026.US

ENCLOSURES (check all that apply)

- | | | |
|---|---|--|
| <input type="checkbox"/> Fee Transmittal Form | <input type="checkbox"/> Assignment Papers (for an Application) | <input type="checkbox"/> After Allowance Communication to Group |
| <input type="checkbox"/> Preliminary Amendment / Response | <input type="checkbox"/> Drawing(s) | <input type="checkbox"/> Appeal Communication to Board of Appeals and Interferences |
| <input type="checkbox"/> After Final Affidavits/declaration(s) | <input type="checkbox"/> Licensing-related Papers | <input type="checkbox"/> Appeal Communication to Group (Appeal Notice, Brief, Reply Brief) |
| <input type="checkbox"/> Extension of Time Request | <input type="checkbox"/> Petition Routing Slip (PTO/SB/69) and Accompanying Petition | <input type="checkbox"/> Proprietary Information |
| <input type="checkbox"/> Express Abandonment Request | <input type="checkbox"/> To Convert a Provisional Application | <input type="checkbox"/> Status Letter |
| <input checked="" type="checkbox"/> Information Disclosure Statement | <input type="checkbox"/> Power of Attorney, Revocation Change of Correspondence Address | <input type="checkbox"/> Additional Enclosure(s) (please identify below): |
| <input type="checkbox"/> Certified Copy of Priority Documents) | <input type="checkbox"/> Terminal Disclaimer | |
| <input type="checkbox"/> Response to Missing Part/ Incomplete Application | <input type="checkbox"/> Request for Refund | |
| <input type="checkbox"/> Response to Missing Parts | | |


REMARKS

SIGNATURE OF APPLICANT, ATTORNEY, OR AGENT

Firm Or Individual name	Jaimes Sher	Registration No.	34,726
Signature			
Date	October 13, 2000		

CERTIFICATE OF MAILING

I hereby certify having information and a reasonable basis for belief that this correspondence will be deposited with the United States Postal Service as first class mail in an envelope addressed to: Assistant Commissioner for Patents, Washington, D.C. 20231 on this date: October 13, 2000

Typed or printed name	Tammy L. Hodges		
Signature		Date	October 13, 2000

[illegible]

ATTY. DOCKET: 2000U026.US

CORRESPONDENCE ADDRESS: Jaimes Sher
Lisa Kimes Jones
Univation Technologies, LLC
5555 San Felipe, Suite 1950
Houston, TX 77056

**A METHOD FOR PREPARING A CATALYST
SYSTEM AND ITS USE IN A POLYMERIZATION PROCESS**

5 FIELD OF THE INVENTION

The present invention relates to a method for preparing a catalyst system and for its use in a process for polymerizing olefin(s). In particular, the invention is directed to a method for preparing a catalyst composition of a supported activator and a metal compound and a bulky ligand.

10

BACKGROUND OF THE INVENTION

Advances in polymerization and catalysis have resulted in the capability to produce many new polymers having improved physical and chemical properties useful in a wide variety of superior products and applications. With the
15 development of new catalysts the choice of polymerization-type (solution, slurry, high pressure or gas phase) for producing a particular polymer has greatly expanded. Also, advances in polymerization technology have provided more efficient, highly productive and economically enhanced processes. Especially illustrative of these advances is the development of technology utilizing bulky
20 ligand metallocene catalyst systems. In particular, in a slurry or gas phase process where typically a supported catalyst system is used, there are a variety of different methods described in the art for supporting bulky ligand metallocene catalyst systems.

Illustrative methods for producing supported bulky ligand metallocene
25 catalyst systems include: U.S. Patent No. 5,332,706 and 5,473,028 have resorted to a particular technique for forming a catalyst by incipient impregnation; U.S. Patent Nos. 5,427,991 and 5,643,847 describe the chemical bonding of non-coordinating anionic activators to supports; U.S. Patent No. 5,492,975 discusses polymer bound metallocene catalyst systems; PCT publication WO 97/06186
30 published February 20, 1997 teaches removing inorganic and organic impurities after formation of the metallocene catalyst itself; PCT publication WO 97/15602 published May 1, 1997 discusses readily supportable metal complexes; U.S. Patent No. 4,937,217 generally describes a mixture of trimethylaluminum and triethylaluminum added to an undehydrated silica then adding a metallocene
35 catalyst; EP-B1-0 308 177 generally describes adding a wet monomer to a reactor containing a metallocene, trialkylaluminum and undehydrated silica; U.S. Patent

Nos. 4,912,075, 4,935,397 and 4,937,301 generally relate to adding trimethylaluminum to an undehydrated silica and then adding a metallocene to form a dry supported catalyst; U.S. Patent No. 4,914,253 describes adding trimethylaluminum to undehydrated silica, adding a metallocene and then drying
5 the catalyst with an amount of hydrogen to produce a polyethylene wax; U.S. Patent Nos. 5,008,228, 5,086,025 and 5,147,949 generally describe forming a dry supported catalyst by the addition of trimethylaluminum to a water impregnated silica to form alumoxane in situ and then adding the metallocene; U.S. Patent Nos. 4,808,561, 4,897,455 and 4,701,432 describe techniques to form a supported
10 catalyst where the inert carrier, typically silica, is calcined and contacted with a metallocene(s) and a activator/cocatalyst component; U.S. Patent No. 5,238,892 describes forming a dry supported catalyst by mixing a metallocene with an alkyl aluminum then adding undehydrated silica; and U.S. Patent No. 5,240,894 generally pertains to forming a supported metallocene/alumoxane catalyst system
15 by forming a metallocene/alumoxane reaction solution, adding a porous carrier, and evaporating the resulting slurry to remove residual solvent from the carrier.

There are a variety of techniques discussed for preparing a supported activator and to its use in a catalyst system for polymerizing olefin(s). The following non-limiting examples of patent publications discussing supported
20 activators, which are all fully incorporated herein by reference, include: U.S. Patent No. 5,728,855 directed to the forming a supported oligomeric alkylaluminumoxane formed by treating a trialkylaluminum with carbon dioxide prior to hydrolysis; U.S. Patent No. 5,831,109 and 5,777,143 discusses a supported methylalumoxane made using a non-hydrolytic process; U.S. Patent
25 No. 5,731,451 relates to a process for making a supported alumoxane by oxygenation with a trialkylsiloxy moiety; U.S. Patent No. 5,856,255 discusses forming a supported auxiliary catalyst (alumoxane or organoboron compound) at elevated temperatures and pressures; U.S. Patent No. 5,739,368 discusses a process of heat treating alumoxane and placing it on a support; EP-A-0 545 152
30 relates to adding a metallocene to a supported alumoxane and adding more methylalumoxane; U.S. Patent Nos. 5,756,416 and 6,028,151 discuss a catalyst composition of a alumoxane impregnated support and a metallocene and a bulky aluminum alkyl and methylalumoxane; EP-B1-0 662 979 discusses the use of a metallocene with a catalyst support of silica reacted with alumoxane; PCT WO
35 96/16092 relates to a heated support treated with alumoxane and washing to

remove unfixed alumoxane; U.S. Patent Nos. 4,912,075, 4,937,301, 5,008,228, 5,086,025, 5,147,949, 4,871,705, 5,229,478, 4,935,397, 4,937,217 and 5,057,475, and PCT WO 94/26793 all directed to adding a metallocene to a supported activator; U.S. Patent No. 5,902,766 relates to a supported activator having a
5 specified distribution of alumoxane on the silica particles; U.S. Patent No. 5,468,702 relates to aging a supported activator and adding a metallocene; U.S. Patent No. 5,968,864 discusses treating a solid with alumoxane and introducing a metallocene; EP 0 747 430 A1 relates to a process using a metallocene on a supported methylalumoxane and trimethylaluminum; EP 0 969 019 A1 discusses
10 the use of a metallocene and a supported activator; EP-B2-0 170 059 relates to a polymerization process using a metallocene and a organo-aluminum compound, which is formed by reacting aluminum trialkyl with a water containing support; U.S. Patent No. 5,212,232 discusses the use of a supported alumoxane and a metallocene for producing styrene based polymers; U.S. Patent No. 5,026,797
15 discusses a polymerization process using a solid component of a zirconium compound and a water-insoluble porous inorganic oxide preliminarily treated with alumoxane; U.S. Patent No. 5,910,463 relates to a process for preparing a catalyst support by combining a dehydrated support material, an alumoxane and a polyfunctional organic crosslinker; U.S. Patent Nos. 5,332,706, 5,473,028,
20 5,602,067 and 5,420,220 discusses a process for making a supported activator where the volume of alumoxane solution is less than the pore volume of the support material; WO 98/02246 discusses silica treated with a solution containing a source of aluminum and a metallocene; WO 99/03580 relates to the use of a supported alumoxane and a metallocene; EP-A1-0 953 581 discloses a
25 heterogeneous catalytic system of a supported alumoxane and a metallocene; U.S. Patent No. 5,015,749 discusses a process for preparing a polyhydrocarbylalumoxane using a porous organic or inorganic imbibitor material; U.S. Patent Nos. 5,446,001 and 5,534,474 relates to a process for preparing one or more alkylaluminumoxanes immobilized on a solid, particulate inert support; and EP-
30 A1-0 819 706 relates to a process for preparing a solid silica treated with alumoxane. Also, the following articles, also fully incorporated herein by reference for purposes of disclosing useful supported activators and methods for their preparation, include: W. Kaminsky, et al., "Polymerization of Styrene with Supported Half-Sandwich Complexes", Journal of Polymer Science Vol. 37,
35 2959-2968 (1999) describes a process of adsorbing a methylalumoxane to a

support followed by the adsorption of a metallocene; Junting Xu, et al.

“Characterization of isotactic polypropylene prepared with dimethylsilyl bis(1-indenyl)zirconium dichloride supported on methylaluminoxane pretreated silica”, European Polymer Journal 35 (1999) 1289-1294, discusses the use of silica treated with methylaluminoxane and a metallocene; Stephen O’Brien, et al., “EXAFS analysis of a chiral alkene polymerization catalyst incorporated in the mesoporous silicate MCM-41” Chem. Commun. 1905-1906 (1997) discloses an immobilized alumoxane on a modified mesoporous silica; and F.Bonini, et al., “Propylene Polymerization through Supported Metallocene/MAO Catalysts: Kinetic Analysis and Modeling” Journal of Polymer Science, Vol. 33 2393-2402 (1995) discusses using a methylaluminoxane supported silica with a metallocene.

While all these methods have been described in the art, a need for an improved method for preparing supported bulky ligand metallocene catalysts has been discovered.

SUMMARY OF THE INVENTION

This invention provides a method of making a new and improved supported bulky ligand metallocene catalyst system and for its use in a polymerizing process.

In one embodiment, the invention relates to a method for making a supported catalyst system comprising the steps of: (a) forming a supported activator; (b) introducing a bulky ligand; and introducing a metal compound.

In another aspect, the invention is directed to a method for making a supported catalyst system comprising the steps of: (a) combining a support material with an activator; (b) adding a bulky ligand; and (c) adding a metal compound. In this embodiment it is preferred to complete step (a) to form a supported activator prior to steps (b) and (c).

In another embodiment, the invention is directed to a process for polymerizing olefin(s), particularly in a gas phase or slurry phase process, utilizing the supported catalyst systems prepared by the above described methods.

In one embodiment, the invention is directed to a process for polymerizing olefin(s) in the presence of a catalyst system, the catalyst system comprising the combination of a supported activator, a bulky ligand, and a metal compound. In this embodiment, it is preferred that the supported activator is combined with the

bulky ligand and the metal compound prior to their introduction to a polymerization reactor.

In yet another embodiment, the invention is to a process for polymerizing olefin(s) in a reactor in the presence of a catalyst system comprising an activator, a support material, a bulky ligand and a metal compound. Preferably in this embodiment, the activator and the support material are first combined to form a supported activator.

DETAILED DESCRIPTION OF THE INVENTION

Introduction

The invention is directed toward a method for making and using a supported catalyst system. It has been surprisingly discovered that contacting a supported activator with a bulky ligand and a metal compound results in an active polymerization catalyst. While not wishing to be bound to any particular theory it is believed that in the presence of the supported activator the bulky ligand and the metal compound, complex, or "self-assemble", into an active olefin polymerization catalyst. However, for purposes of this patent specification and appended claims, a bulky ligand and metal compound are separate components and are not the equivalent to a preformed bulky ligand metallocene-type compound. The method of the invention provides a simple route to producing a supported catalyst system without the need to synthesize, for example, a bulky ligand metallocene catalyst compound. Furthermore, the invention provides for the flexibility for easily changing the bulky ligand without the need for synthesizing another bulky ligand metallocene type catalyst compound. This capability has many advantages including mixed catalyst technologies, especially where two or more bulky ligand metallocene-type catalysts are utilized.

Bulky Ligands

The bulky ligands of the invention are generally represented by one or more open, acyclic, or fused ring(s) or ring system(s) or a combination thereof. These bulky ligands, preferably the ring(s) or ring system(s) are typically composed of atoms selected from Groups 13 to 16 atoms of the Periodic Table of Elements, preferably the atoms are selected from the group consisting of carbon, nitrogen, oxygen, silicon, sulfur, phosphorous, germanium, boron and aluminum or a combination thereof. Most preferably the ring(s) or ring system(s) are composed of carbon atoms such as but not limited to those cycloalkadiene or other

similar functioning precursors capable of forming a bulky ligand such as a cyclopentadienyl ligand or cyclopentadienyl-type ligand structure or other specific similar functioning ligand structure such as a pentadiene, cyclopentadiene, indene, pentamethylcyclopentadiene, fluorine, fulvenes, a cyclooctatetraendiyl or an imide
5 ligand. The metal atom is preferably selected from Groups 3 through 15 and the lanthanide or actinide series of the Periodic Table of Elements.

The bulky ligands are open, acyclic or fused ring(s) or ring system(s) such as unsubstituted or substituted, cyclopentadienyl ligands or cyclopentadienyl-type ligands, heteroatom substituted and/or heteroatom containing cyclopentadienyl-
10 type ligands. Non-limiting examples of bulky ligands include cyclopentadienyl ligands, cyclopentaphenan-threnyl ligands, indenyl ligands, benzindenyl ligands, fluorenyl ligands, octahydro-fluorenyl ligands, cyclooctatetraendiyl ligands, cyclopentacyclododecene ligands, azenyl ligands, azulene ligands, pentalene ligands, phosphoyl ligands, pyrrolyl ligands, pyrozolyl ligands, carbazolyl
15 ligands, borabenzene ligands and the like, including hydrogenated versions thereof, for example tetrahydroindenyl ligands.

In one embodiment, the bulky ligands are any ligand structure capable of η -bonding, preferably η^3 -bonding and most preferably η^5 -bonding, preferably to the metal of the metal compounds discussed below.

20 In yet another embodiment, the atomic molecular weight (MW) of the bulky ligands exceeds 60 a.m.u., preferably greater than 65 a.m.u..

In another embodiment, the bulky ligands may comprise one or more heteroatoms, for example, nitrogen, silicon, boron, germanium, sulfur and phosphorous, in combination with carbon atoms to form an open, acyclic, or
25 preferably a fused, ring or ring system, for example, a hetero-cyclopentadienyl ancillary ligand. Other bulky ligands include but are not limited to bulky amides, phosphides, alkoxides, aryloxides, imides, carbolides, borollides, porphyrins, phthalocyanines, corrins and other polyazomacrocycles.

In one embodiment, two or more bulky ligands are utilized. In this
30 embodiment, the bulky ligands may be the same or different.

Each bulky ligand may be unsubstituted or substituted with a combination of substituent groups R. Non-limiting examples of substituent groups R include one or more from the group selected from hydrogen, or linear, branched alkyl radicals, or alkenyl radicals, alkynyl radicals, cycloalkyl radicals or aryl radicals,
35 acyl radicals, aroyl radicals, alkoxy radicals, aryloxy radicals, alkylthio radicals,

dialkylamino radicals, alkoxycarbonyl radicals, aryloxycarbonyl radicals, carbomoyl radicals, alkyl- or dialkyl- carbamoyl radicals, acyloxy radicals, acylamino radicals, aroylamino radicals, straight, branched or cyclic, alkylene radicals, or combination thereof. In a preferred embodiment, substituent groups R

5 have up to 50 non-hydrogen atoms, preferably from 1 to 30 carbon, that can also be substituted with halogens or heteroatoms or the like. Non-limiting examples of alkyl substituents R include methyl, ethyl, propyl, butyl, pentyl, hexyl, cyclopentyl, cyclohexyl, benzyl or phenyl groups and the like, including all their isomers, for example tertiary butyl, isopropyl, and the like. Other hydrocarbyl

10 radicals include fluoromethyl, fluroethyl, difluroethyl, iodopropyl, bromohexyl, chlorobenzyl and hydrocarbyl substituted organometalloid radicals including trimethylsilyl, trimethylgermyl, methyldiethylsilyl and the like; and halocarbyl-substituted organometalloid radicals including tris(trifluoro-methyl) silyl, methyl-bis(difluoromethyl)silyl, bromomethyldimethylgermyl and the like; and

15 disubstituted boron radicals including dimethylboron for example; and disubstituted pnictogen radicals including dimethylamine, dimethylphosphine, diphenylamine, methylphenylphosphine, chalcogen radicals including methoxy, ethoxy, propoxy, phenoxy, methylsulfide and ethylsulfide. Non-hydrogen substituents R include the atoms carbon, silicon, boron, aluminum, nitrogen,

20 phosphorous, oxygen, tin, sulfur, germanium and the like, including olefins such as but not limited to olefinically unsaturated substituents including vinyl-terminated ligands, for example but-3-enyl, prop-2-enyl, hex-5-enyl and the like. Also, at least two R groups, preferably two adjacent R groups, are joined to form a ring structure having from 3 to 30 atoms selected from carbon, nitrogen, oxygen,

25 phosphorous, silicon, germanium, aluminum, boron or a combination thereof. Also, a substituent group R group such as 1-butanyl may form a carbon sigma bond to the metal M.

In another embodiment, two or more bulky ligands may be bridged to each other through a bridging groups. Non-limiting examples of bridging groups

30 include bridging groups containing at least one Group 13 to 16 atom, often referred to as a divalent moiety such as but not limited to at least one of a carbon, oxygen, nitrogen, silicon, boron, germanium and tin atom or a combination thereof. Preferably bridging groups contain a carbon, silicon or germanium atom, most preferably at least one silicon atom or at least one carbon atom. The

35 bridging group may also contain substituent groups R as defined above including

halogens. Non-limiting examples of bridging groups may be represented by R'_2C , R'_2Si , $R'_2Si R'_2Si$, R'_2Ge , $R'P$, where R' is independently, a radical group which is hydride, hydrocarbyl, substituted hydrocarbyl, halocarbyl, substituted halocarbyl, hydrocarbyl-substituted organometalloid, halocarbyl-substituted organometalloid, disubstituted boron, disubstituted pnictogen, substituted chalcogen, or halogen.

Metal Compounds

The metal compounds of the invention are preferably transition metal compounds where the metal is selected from Groups 4 through 12, preferably Groups 4, 5 and 6, more preferably the transition metal is from Group 4, most preferably titanium, zirconium or hafnium. In another embodiment, the metal compound of the invention is a transition metal compound where the metal is selected from the group consisting of zirconium, titanium, hafnium, chromium and vanadium.

Other ligands may be bonded to the metal, for example, a monoanionic ligand that is sigma-bonded to the metal. Non-limiting examples of ligands that are bonded or complexed to the metal include weak bases such as amines, phosphines, ethers, carboxylates, dienes, hydrocarbyl radicals having from 1 to 50 carbon atoms, hydrides or halogens and the like or a combination thereof. In another embodiment, two or more of these ligands bonded to the metal form a part of a fused ring or ring system. Other examples of ligands bonded to the metal include those substituents for R as described above and including cyclobutyl, cyclohexyl, heptyl, tolyl, trifluoromethyl, tetramethylene, pentamethylene, methylened, methoxy, ethoxy, propoxy, phenoxy, bis(N-methyl-anilide), dimethylamide, dimethylphosphide radicals and the like.

Other bulky ligands and metal compounds are described in U.S. Patent Nos. 5,064,802, 5,145,819, 5,149,819, 5,243,001, 5,239,022, 5,276,208, 5,296,434, 5,321,106, 5,329,031, 5,304,614, 5,677,401, 5,723,398, 5,753,578, 5,854,363, 5,856,547, 5,858,903, 5,859,158 and 5,900,517 and PCT publications WO 93/08221, WO 93/08199, WO 95/07140, WO 98/11144, WO 98/41530, WO 98/41529, WO 98/46650, WO 99/02540, WO 99/14221, WO 00/35973 and WO 00/35928 and European publications EP-A-0 578 838, EP-A-0 638 595, EP-B-0 513 380, EP-A1-0 816 372, EP-A2-0 839 834, EP-B1-0 632 819, EP-B1-0 748 821 and EP-B1-0 757 996, all of which are herein fully incorporated by reference.

Also bulky ligands and metal compounds are further discussed in PCT publication WO 92/00333, WO 94/07928, WO 91/ 04257, WO 94/03506,

WO96/00244, WO 97/15602, WO 96/33202, WO 96/34021, WO 97/17379, WO 98/22486, WO 99/20637 and WO 00/11006 (metalloid salt catalyst) and U.S. Patent Nos. 5,057,475, 5,096,867, 5,055,438, 5,198,401, 5,227,440, 5,637,660, 5,539,124, 5,554,775, 5,756,611, 5,233,049, 5,744,417, 5,856,258, 5,264,405, 6,066,704, 6,069,237(open pentadienyl ligand), 6,072,067(bulky ligand substituted with a heteroatom), 6,087,515 and 6,090,739 and European publication EP-A-0 420 436 and EP-A1-0 874 005, all of which are herein fully incorporated by reference.

In another embodiment, the bulky ligands include those bidentate ligands containing pyridine or quinoline moieties, such as those described in U.S. Application Serial No. 09/103,620 filed June 23, 1998, or those bulky ligands described in PCT publications WO 99/01481 and WO 98/42664, which are fully incorporated herein by reference.

It is within the scope of this invention, in one embodiment, that the bulky ligands and metal compounds include those complexes of Ni^{2+} and Pd^{2+} described in the articles Johnson, et al., "New Pd(II)- and Ni(II)- Based Catalysts for Polymerization of Ethylene and α -Olefins", J. Am. Chem. Soc. 1995, 117, 6414-6415 and Johnson, et al., "Copolymerization of Ethylene and Propylene with Functionalized Vinyl Monomers by Palladium(II) Catalysts", J. Am. Chem. Soc., 1996, 118, 267-268, and WO 96/23010 published August 1, 1996, WO 99/02472, U.S. Patent Nos. 5,852,145, 5,866,663 and 5,880,241, which are all herein fully incorporated by reference.

Also included as bulky ligands are those diimine based ligands of Group 8 to 10 metal compounds disclosed in PCT publications WO 96/23010, WO 97/48735 and WO 98/40374 and Gibson, et. al., Chem. Comm., pp. 849-850 (1998), all of which are herein incorporated by reference.

Other bulky ligands and metal compounds are described in EP-A2-0 816 384 and U.S. Patent No. 5,851,945, which is incorporated herein by reference. In addition, the bulky ligands include bridged bis(arylamido) ligands described by D.H. McConville, et al., in Organometallics 1195, 14, 5478-5480, which is herein incorporated by reference and bis(hydroxy aromatic nitrogen ligands) described in U.S. Patent No. 5,852,146, which is incorporated herein by reference.

In one embodiment, the metal compounds of the invention are represented by the formula: ML_x

where M is metal from Group 3 to 12 of the Periodic Table of Elements, preferably from Group 4 to 10, more preferably from Group 4 to 6, and most preferably from Group 4, especially zirconium, titanium or hafnium; L is the same or different and is selected from the group consisting of hydrogen, halogen, hydrocarbyl, alkoxide, aryoxide, carboxylate, carbodionate, amide, carbamate, phosphide and the like; and "x" is an integer depending on the valence state of metal, preferably such that the metal compound is a neutral compound, where "x" is equal to the valence state of the metal.

- 10 Non-limiting preferred metal compounds include: ZrCl_4 , ZrBr_4 , ZrI_4 , $\text{Zr}(\text{CH}_2\text{C}_6\text{H}_5)_4$, $\text{Zr}[\text{CH}_2\text{C}(\text{CH}_3)_2\text{C}_6\text{H}_5]_4$, $\text{Zr}[\text{CH}_2\text{Si}(\text{CH}_3)_3]_4$, $\text{Zr}(\text{acetylacetonate})_4$, $\text{Zr}(2,2,6,6\text{-tetramethyl-3,5-heptanedionate})_4$, $\text{Zr}(\text{F})_3(\text{acetylacetonate})$, $\text{Zr}(\text{ethoxide})_4$, $\text{Zr}(\text{t-butoxide})_4$, $\text{Zr}(\text{phenoxide})_4$, $\text{Zr}(\text{NMe}_2)_4$, (Me is methyl), $\text{Zr}(\text{NEt}_2)_4$, (Et is ethyl) $\text{Zr}(\text{diethylcarbamate})_4$, $\text{Zr}(\text{dimethylcarbamate})_4$, $\text{Zr}(\text{pivalate})_4$, $\text{Zr}(\text{benzoate})_4$.

Activators

- For the purposes of this patent specification and appended claims, the term "activator" is defined to be any compound or component or method which can activate any of the bulky ligand(s) and metal compound combinations of the invention for the polymerization of olefin(s).

- Non-limiting activators, for example include a Lewis acid or a non-coordinating ionic activator or ionizing activator or any other compound including Lewis bases, aluminum alkyls, conventional-type cocatalysts and combinations thereof. It is within the scope of this invention to use alumoxane or modified alumoxane as an activator, and/or to also use ionizing activators, neutral or ionic, such as tri (n-butyl) ammonium tetrakis (pentafluorophenyl) boron, a trisperfluorophenyl boron metalloid precursor or a trisperfluoronaphthyl boron metalloid precursor, polyhalogenated heteroborane anions (WO 98/43983) or combination thereof.

- There are a variety of methods for preparing alumoxane and modified alumoxanes, non-limiting examples of which are described in U.S. Patent No. 4,665,208, 4,952,540, 5,091,352, 5,206,199, 5,204,419, 4,874,734, 4,924,018, 4,908,463, 4,968,827, 5,308,815, 5,329,032, 5,248,801, 5,235,081, 5,157,137, 5,103,031, 5,391,793, 5,391,529, 5,693,838, 5,731,253, 5,731,451, 5,744,656, 5,847,177, 5,854,166 and 5,856,256 and European publications EP-A-0 561 476,

EP-B1-0 279 586, EP-A-0 594-218 and EP-B1-0 586 665, and PCT publication WO 94/10180, all of which are herein fully incorporated by reference. Other alumoxanes include siloxy alumoxanes as described in EP-B1-0 621 279 and U.S. Patent No. 6,060,418, and chemically functionalized carboxylate-alumoxane
5 described in WO 00/09578, which are herein incorporated by reference.

Organoaluminum compounds as activators include trimethylaluminum, triethylaluminum, triisobutylaluminum, tri-n-hexylaluminum, tri-n-octylaluminum and the like.

Ionizing compounds may contain an active proton, or some other cation
10 associated with but not coordinated to or only loosely coordinated to the remaining ion of the ionizing compound. Such compounds and the like are described in European publications EP-A-0 570 982, EP-A-0 520 732, EP-A-0 495 375, EP-B1-0 500 944, EP-A-0 277 003 and EP-A-0 277 004, and U.S. Patent Nos. 5,153,157, 5,198,401, 5,066,741, 5,206,197, 5,241,025, 5,384,299,
15 5,502,124 and 6,087,460 and U.S. Patent Application Serial No. 08/285,380, filed August 3, 1994, all of which are herein fully incorporated by reference.

Other activators include those described in PCT publication WO 98/07515 such as tris (2, 2', 2''- nonafluorobiphenyl) fluoroaluminate, which publication is fully incorporated herein by reference. Combinations of activators are also
20 contemplated by the invention, for example, alumoxanes and ionizing activators in combinations, see for example, EP-B1 0 573 120, PCT publications WO 94/07928 and WO 95/14044 and U.S. Patent Nos. 5,153,157 and 5,453,410 all of which are herein fully incorporated by reference. WO 98/09996 incorporated herein by reference describes activating metal compounds with perchlorates,
25 periodates and iodates including their hydrates. WO 98/30602 and WO 98/30603 incorporated by reference describe the use of lithium (2,2'-bisphenyl-ditrimethylsilicate)•4THF as an activator. EP-A2-0 103 675 describes fluorinated organic compound activators, which is herein incorporated by reference. WO 99/18135 incorporated herein by reference describes the use of organo-boron-
30 aluminum activators. EP-B1-0 781 299 describes using a silylium salt in combination with a non-coordinating compatible anion. Other activators are described in for example, U.S. Patent Nos. 5,849,852, 5,859,653, 5,869,723 and 6,030,917 (gallium based anion activators) and PCT WO 98/32775, WO 00/09513 (three coordinate aluminum activator) and WO 00/20115, which are herein
35 incorporated by reference.

Supports Materials

Any of the conventional support materials are useful in this invention. Preferably the supported material is a porous support material, for example, talc, inorganic oxides and inorganic chlorides. Other support materials include
5 resinous support materials such as polystyrene, functionalized or crosslinked organic supports, such as polystyrene divinyl benzene polyolefins or polymeric compounds, zeolites, clays, or any other organic or inorganic support material and the like, or mixtures thereof.

The preferred support materials are inorganic oxides that include those
10 Group 2, 3, 4, 5, 13 or 14 metal oxides. The preferred support materials include silica, alumina, silica-alumina, magnesium chloride, and mixtures thereof. Other useful support materials include magnesia, titania, zirconia, montmorillonite (EP-B1 0 511 665), hydrotalcites, and the like. Also, combinations of these support materials may be used, for example, silica-chromium, silica-alumina, silica-titania
15 and the like.

It is preferred that the support material, most preferably an inorganic oxide, has a surface area in the range of from about 10 to about 700 m²/g, pore volume in the range of from about 0.1 to about 4.0 cc/g and average particle size in the range of from about 5 to about 500 µm. More preferably, the surface area
20 of the support material is in the range of from about 50 to about 500 m²/g, pore volume of from about 0.5 to about 3.5 cc/g and average particle size of from about 10 to about 200 µm. Most preferably the surface area of the support material is in the range is from about 100 to about 400 m²/g, pore volume from about 0.8 to about 3.0 cc/g and average particle size is from about 5 to about 100 µm. The
25 average pore size of the carrier of the invention typically has pore size in the range of from 10 to 1000Å, preferably 50 to about 500Å, and most preferably 75 to about 350Å.

The support materials may be treated chemically, for example with a fluoride compound as described in WO 00/12565, which is herein incorporated by
30 reference.

Supported Activators

The above-described activators may be combined with one or more support materials also described above using one or more support methods well known in the art. For example, in a most preferred embodiment, an activator is

deposited on, contacted with, or incorporated within, vaporized onto, reacted with, adsorbed or absorbed in, or on, a support material.

Other supported activators are described in for example WO 00/13792 that refers to supported boron containing solid acid complex.

5 In a preferred method of forming the supported activator the amount of liquid in which the activator is present is in an amount that is less than four times the pore volume of the support material, more preferably less than three times, even more preferably less than two times; preferred ranges being from 1.1 times to 3.5 times range and most preferably in the 1.2 to 3 times range. In an alternative
10 embodiment, the amount of liquid in which the activator is present is from one to less than one times the pore volume of the support material utilized in forming the supported activator.

 Procedures for measuring the total pore volume of a porous support are well known in the art. Details of one of these procedures is discussed in Volume
15 1, *Experimental Methods in Catalytic Research* (Academic Press, 1968) (specifically see pages 67-96). This preferred procedure involves the use of a classical BET apparatus for nitrogen absorption. Another method well known in the art is described in Innes, *Total Porosity and Particle Density of Fluid Catalysts By Liquid Titration*, Vol. 28, No. 3, *Analytical Chemistry* 332-334
20 (March, 1956).

 In an embodiment, the supported activator is in a dried state, a solid. In another embodiment, the supported activator is in a substantially dry state or a slurry, preferably in a mineral oil slurry.

 In another embodiment, two or more separately supported activators are
25 used, or alternatively, two or more different activators on a single support are used, in combination with a bulky ligand and a metal compound.

Supported Catalyst System

 The supported catalyst system of the invention generally involves the combining, contacting, vaporizing, blending, bonding and/or mixing any of the
30 above described supported activators, bulky ligands and metal compounds in any order.

 In one embodiment of the method of the invention the supported activator is combined with the bulky ligand prior to the addition of the metal compound. In another embodiment, the bulky ligand and the metal compound are contacted first,
35 and then combined with the supported activator. In an alternate embodiment, an

activator is combined with the bulky ligand and/or metal compound to form a mixture, and then the mixture is added to the support material.

In one embodiment, the supported activator is contacted with two or more bulky ligands with one or more metal compounds. In one embodiment, the two
5 bulky ligands are the same and one type of metal compound is used. In another embodiment, two different bulky ligands, in type or having different substituents are used in combination with one metal compound, or two different metal compounds.

In another embodiment the combined amount in weight percent of the
10 supported activator to the bulky ligand and metal compound are in the range of from 99.9 weight percent to 50 weight percent, preferably from about 99.8 weight percent to about 60 weight percent, more preferably from about 99.7 weight percent to about 70 weight percent, and most preferably from about 99.6 weight percent to about 80 weight percent.

In yet another embodiment, the mole ratio of the metal compound to the
15 bulky ligand is in the range of from 0.01 to 100, preferably from 0.02 to 50, more preferably 0.05 to 20, most preferably 0.1 to 10.

In yet another embodiment the mole ratio of the metal of the activator to the metal of the metal compound is in the range of from 5000 to 1, preferably
20 from about 2000 to 2, more preferably from about 1000 to about 5, and most preferably from about 500 to about 10.

Where the activator contains aluminum, preferably an alumoxane, the mole ratio of the metal of the activator component to the metal of the metal
25 compound are in the range of between 0.3:1 to 1000:1, preferably 20:1 to 800:1, and most preferably 50:1 to 500:1.

Where the activator is an ionizing activator such as those based on the anion tetrakis(pentafluorophenyl)boron, the mole ratio of the metal of the
activator component to the metal component of the bulky ligand metallocene catalyst is preferably in the range of between 0.3:1 to 3:1.

In other embodiments of the invention the supported activator is in a dry or
30 substantially dried state, or in a solution, when contacted with the bulky ligand and the metal compound. The resulting supported catalyst system is used in a dry or substantially dry state, or as a slurry, in preferably a mineral oil. Also, the dried supported catalyst system of the invention can be reslurried in a liquid such as

mineral oil, toluene, or any the hydrocarbon prior to its introduction into a polymerization reactor.

Furthermore, it is contemplated that the supported activator, bulky ligand, and metal compound can be used in the same solvents or different solvents. For example, the bulky ligands can be in toluene, the metal compound in isopentane and the supported activator in mineral oil, or any combination of solvents.

Preferably the contact temperature for combining the supported activator, bulky ligand and metal compound is in the range of from 0 °C to about 100 °C, more preferably from 15 °C to about 75 °C, most preferably at about ambient temperature and pressure.

Preferably, the supported activator is contacted with the bulky ligand and the metal compound for a period of time greater than a second, preferably from about 1 minute to about 48 hours, more preferably from about 10 minutes to about 10 hours, and most preferably from about 30 minutes to about 6 hours. The period of contacting refers to the mixing time only.

Antistatic agents or surface modifiers may be used in combination with the supported activator, bulky ligand and metal compound of the invention, see for example those agents and modifiers described in PCT publication WO 96/11960, which is herein fully incorporated by reference. Also, a carboxylic acid salt of a metal ester, for example aluminum carboxylates such as aluminum mono, di- and tri- stearates, aluminum octoates, oleates and cyclohexylbutyrates, as described in U.S. Application Serial No. 09/113,216, filed July 10, 1998 may be used in combination with a supported activator, a bulky ligand and a metal compound.

In one embodiment of the invention, olefin(s), preferably C₂ to C₃₀ olefin(s) or alpha-olefin(s), preferably ethylene or propylene or combinations thereof are prepolymerized in the presence of the supported activator, bulky ligand and metal compound combination prior to the main polymerization. The prepolymerization can be carried out batchwise or continuously in gas, solution or slurry phase including at elevated pressures. The prepolymerization can take place with any olefin monomer or combination and/or in the presence of any molecular weight controlling agent such as hydrogen. For examples of prepolymerization procedures, see U.S. Patent Nos. 4,748,221, 4,789,359, 4,923,833, 4,921,825, 5,283,278 and 5,705,578 and European Publication EP-B1-0 279 863 and PCT Publication WO 97/44371, and all of which are herein fully incorporated by reference.

Polymerization Process

The supported catalyst system or composition of the invention described above are suitable for use in any polymerization process over a wide range of temperatures and pressures. The temperatures may be in the range of from -60 °C
5 to about 280°C, preferably from 50°C to about 200°C, and the pressures employed may be in the range from 1 atmosphere to about 500 atmospheres or higher.

Polymerization processes include solution, gas phase, slurry phase and a high pressure process or a combination thereof. Particularly preferred is a gas phase or slurry phase polymerization of one or more olefins at least one of which
10 is ethylene or propylene.

In one embodiment, the process of this invention is directed toward a solution, high pressure, slurry or gas phase polymerization process of one or more olefin monomers having from 2 to 30 carbon atoms, preferably 2 to 12 carbon atoms, and more preferably 2 to 8 carbon atoms. The invention is particularly
15 well suited to the polymerization of two or more olefin monomers of ethylene, propylene, butene-1, pentene-1, 4-methyl-pentene-1, hexene-1, octene-1 and decene-1.

Other monomers useful in the process of the invention include ethylenically unsaturated monomers, diolefins having 4 to 18 carbon atoms, conjugated or nonconjugated dienes, polyenes, vinyl monomers and cyclic olefins.
20 Non-limiting monomers useful in the invention may include norbornene, norbornadiene, isobutylene, isoprene, vinylbenzocyclobutane, styrenes, alkyl substituted styrene, ethylidene norbornene, dicyclopentadiene and cyclopentene.

In the most preferred embodiment of the process of the invention, a
25 copolymer of ethylene is produced, where with ethylene, a comonomer having at least one alpha-olefin having from 4 to 15 carbon atoms, preferably from 4 to 12 carbon atoms, and most preferably from 4 to 8 carbon atoms, is polymerized in a gas phase process.

In another embodiment of the process of the invention, ethylene or
30 propylene is polymerized with at least two different comonomers, optionally one of which may be a diene, to form a terpolymer.

In one embodiment, the invention is directed to a polymerization process, particularly a gas phase or slurry phase process, for polymerizing propylene alone or with one or more other monomers including ethylene, and/or other olefins
35 having from 4 to 12 carbon atoms. Polypropylene polymers may be produced

using the particularly bridged bulky ligands and metal compounds as described in U.S. Patent Nos. 5,296,434 and 5,278,264, both of which are herein incorporated by reference.

Typically in a gas phase polymerization process a continuous cycle is employed where in one part of the cycle of a reactor system, a cycling gas stream, otherwise known as a recycle stream or fluidizing medium, is heated in the reactor by the heat of polymerization. This heat is removed from the recycle composition in another part of the cycle by a cooling system external to the reactor. Generally, in a gas fluidized bed process for producing polymers, a gaseous stream containing one or more monomers is continuously cycled through a fluidized bed in the presence of a catalyst under reactive conditions. The gaseous stream is withdrawn from the fluidized bed and recycled back into the reactor. Simultaneously, polymer product is withdrawn from the reactor and fresh monomer is added to replace the polymerized monomer. (See for example U.S. Patent Nos. 4,543,399, 4,588,790, 5,028,670, 5,317,036, 5,352,749, 5,405,922, 5,436,304, 5,453,471, 5,462,999, 5,616,661 and 5,668,228, all of which are fully incorporated herein by reference.)

The reactor pressure in a gas phase process may vary from about 100 psig (690 kPa) to about 500 psig (3448 kPa), preferably in the range of from about 200 psig (1379 kPa) to about 400 psig (2759 kPa), more preferably in the range of from about 250 psig (1724 kPa) to about 350 psig (2414 kPa).

The reactor temperature in a gas phase process may vary from about 30°C to about 120°C, preferably from about 60°C to about 115°C, more preferably in the range of from about 70°C to 110°C, and most preferably in the range of from about 70°C to about 95°C.

Other gas phase processes contemplated by the process of the invention include series or multistage polymerization processes. Also gas phase processes contemplated by the invention include those described in U.S. Patent Nos. 5,627,242, 5,665,818 and 5,677,375, and European publications EP-A- 0 794 200 EP-B1-0 649 992, EP-A- 0 802 202 and EP-B- 0 634 421 all of which are herein fully incorporated by reference.

In a preferred embodiment, the reactor utilized in the present invention is capable and the process of the invention is producing greater than 500 lbs of polymer per hour (227 Kg/hr) to about 200,000 lbs/hr (90,900 Kg/hr) or higher of polymer, preferably greater than 1000 lbs/hr (455 Kg/hr), more preferably greater

than 10,000 lbs/hr (4540 Kg/hr), even more preferably greater than 25,000 lbs/hr (11,300 Kg/hr), still more preferably greater than 35,000 lbs/hr (15,900 Kg/hr), still even more preferably greater than 50,000 lbs/hr (22,700 Kg/hr) and most preferably greater than 65,000 lbs/hr (29,000 Kg/hr) to greater than 100,000 lbs/hr (45,500 Kg/hr).

A slurry polymerization process generally uses pressures in the range of from about 1 to about 50 atmospheres and even greater and temperatures in the range of 0°C to about 120°C. In a slurry polymerization, a suspension of solid, particulate polymer is formed in a liquid polymerization diluent medium to which ethylene and comonomers and often hydrogen along with catalyst are added. The suspension including diluent is intermittently or continuously removed from the reactor where the volatile components are separated from the polymer and recycled, optionally after a distillation, to the reactor. The liquid diluent employed in the polymerization medium is typically an alkane having from 3 to 7 carbon atoms, preferably a branched alkane. The medium employed should be liquid under the conditions of polymerization and relatively inert. When a propane medium is used the process must be operated above the reaction diluent critical temperature and pressure. Preferably, a hexane or an isobutane medium is employed.

A preferred polymerization technique of the invention is referred to as a particle form polymerization, or a slurry process where the temperature is kept below the temperature at which the polymer goes into solution. Such technique is well known in the art, and described in for instance U.S. Patent No. 3,248,179, which is fully incorporated herein by reference. Other slurry processes include those employing a loop reactor and those utilizing a plurality of stirred reactors in series, parallel, or combinations thereof. Non-limiting examples of slurry processes include continuous loop or stirred tank processes. Also, other examples of slurry processes are described in U.S. Patent No. 4,613,484, which is herein fully incorporated by reference.

In an embodiment the reactor used in the slurry process of the invention is capable of and the process of the invention is producing greater than 2000 lbs of polymer per hour (907 Kg/hr), more preferably greater than 5000 lbs/hr (2268 Kg/hr), and most preferably greater than 10,000 lbs/hr (4540 Kg/hr). In another embodiment the slurry reactor used in the process of the invention is producing

Examples of solution processes are described in U.S. Patent Nos. 4,271,060, 5,001,205, 5,236,998 and 5,589,555, which are fully incorporated

A preferred process of the invention is where the process, preferably a slurry or gas phase process is operated in the presence of a bulky ligand metallocene catalyst system of the invention and in the absence of or essentially free of any scavengers, such as triethylaluminum, trimethylaluminum, triisobutylaluminum and tri-n-hexylaluminum and diethyl aluminum chloride, dibutyl zinc and the like. This preferred process is described in PCT publication WO 96/08520 and U.S. Patent No. 5,712,352 and 5,763,543, which are herein fully incorporated by reference.

15 The polymers produced by the process of the invention can be used in a wide variety of products and end-use applications. The polymers produced by the process of the invention include linear low-density polyethylene, elastomers, plastomers, high-density polyethylenes, low-density polyethylenes, polypropylene and polypropylene copolymers.

The polymers produced by the process of the invention typically have a molecular weight distribution, a weight average molecular weight to number average molecular weight (M_w/M_n) of greater than 1.5 to about 15, particularly greater than 2 to about 10, more preferably greater than about 2.2 to less than about 8, and most preferably from 2.5 to 8.

Also, the polymers of the invention typically have a narrow composition distribution as measured by Composition Distribution Breadth Index (CDBI). Further details of determining the CDBI of a copolymer are known to those

skilled in the art. See, for example, PCT Patent Application WO 93/03093, published February 18, 1993, which is fully incorporated herein by reference.

The bulky ligand metallocene catalyzed polymers of the invention in one embodiment have CDBI's generally in the range of greater than 50% to 100%, preferably 99%, preferably in the range of 55% to 85%, and more preferably 60% to 80%, even more preferably greater than 60%, still even more preferably greater than 65%.

In another embodiment, polymers produced using a bulky ligand metallocene catalyst system of the invention have a CDBI less than 50%, more preferably less than 40%, and most preferably less than 30%.

The polymers of the present invention in one embodiment have a melt index (MI) or (I_2) as measured by ASTM-D-1238-E in the range from 0.01 dg/min to 1000 dg/min, more preferably from about 0.01 dg/min to about 100 dg/min, even more preferably from about 0.1 dg/min to about 50 dg/min, and most preferably from about 0.1 dg/min to about 10 dg/min.

The polymers of the invention in an embodiment have a melt index ratio (I_{21}/I_2) (I_{21} is measured by ASTM-D-1238-F) of from 10 to less than 25, more preferably from about 15 to less than 25.

The polymers of the invention in a preferred embodiment have a melt index ratio (I_{21}/I_2) (I_{21} is measured by ASTM-D-1238-F) of from preferably greater than 25, more preferably greater than 30, even more preferably greater than 40, still even more preferably greater than 50 and most preferably greater than 65. In an embodiment, the polymer of the invention may have a narrow molecular weight distribution and a broad composition distribution or vice-versa, and may be those polymers described in U.S. Patent No. 5,798,427 incorporated herein by reference.

In yet another embodiment, propylene based polymers are produced in the process of the invention. These polymers include atactic polypropylene, isotactic polypropylene, hemi-isotactic and syndiotactic polypropylene. Other propylene polymers include propylene block or impact copolymers. Propylene polymers of these types are well known in the art see for example U.S. Patent Nos. 4,794,096, 3,248,455, 4,376,851, 5,036,034 and 5,459,117, all of which are herein incorporated by reference.

The polymers of the invention may be blended and/or coextruded with any other polymer. Non-limiting examples of other polymers include linear low

density polyethylenes produced via conventional Ziegler-Natta and/or bulky ligand metallocene catalysis, elastomers, plastomers, high pressure low density polyethylene, high density polyethylenes, polypropylenes and the like.

5 Polymers produced by the process of the invention and blends thereof are
useful in such forming operations as film, sheet, and fiber extrusion and co-
extrusion as well as blow molding, injection molding and rotary molding. Films
include blown or cast films formed by coextrusion or by lamination useful as
shrink film, cling film, stretch film, sealing films, oriented films, snack packaging,
heavy duty bags, grocery sacks, baked and frozen food packaging, medical
10 packaging, industrial liners, membranes, etc. in food-contact and non-food contact
applications. Fibers include melt spinning, solution spinning and melt blown fiber
operations for use in woven or non-woven form to make filters, diaper fabrics,
medical garments, geotextiles, etc. Extruded articles include medical tubing, wire
and cable coatings, geomembranes, and pond liners. Molded articles include
15 single and multi-layered constructions in the form of bottles, tanks, large hollow
articles, rigid food containers and toys, etc.

EXAMPLES

20 In order to provide a better understanding of the present invention
including representative advantages thereof, the following examples are offered.

Activity values are normalized values based upon grams of polymer
produced per mmol of transition metal in the catalyst per hour per 100 psi (690
kPa) of ethylene polymerization pressure. MI is Melt Index, and was reported as
grams per 10 minutes per ASTM D-1238, Condition E. FI is Flow Index, and was
25 measured 10 times the weight used in the melt index above per ASTM D-1238,
Condition F. MFR is Melt Flow Ratio, and is the ratio of FI:MI.

MAO is methylalumoxane in toluene (30 wt%), available from Albemarle
Corporation, Baton Rouge, Louisiana.

30 Kaydol, a white mineral oil, was purchased from Witco Corporation,
Memphis, Tennessee, and was purified by first degassed with nitrogen for 1 hour,
followed by heating at 80°C under vacuum for 10 hours.

Tetrabenzylzirconium ($\text{Zr}(\text{CH}_2\text{C}_6\text{H}_5)_4$) and bis(indenyl)zirconium
dichloride were purchased from Boulder Scientific Company.

35 Indene and pentamethylcyclopentadiene were purchase from Aldrich
Chemical Company.

Preparation of Supported MAO (SMAO)

A toluene solution of methylalumoxane (MAO) was prepared by mixing 960 g of 30 wt% MAO, (MAO was purchased from Albemarle Corporation, Baton Rouge, Louisiana), in 2.7 liter of dry, degassed toluene. This solution was stirred at ambient temperature while 850 g of silica gel (Davison 955, dehydrated at 600°C available from W.R. Grace, Davison Division, Baltimore, Maryland) was added. The resulting slurry was stirred at ambient temperature for 1 hour and the solvent was removed under reduced pressure with a stream of nitrogen at 85°C. The drying is continued until the material temperature has been constant for 2 hours. The resulting free-flowing white powder has an aluminum loading of 4.1 mmol Al per gram of solid.

Example 2

Preparation of Supported Tetrabenzylzirconium (TBZ) (Composition A)

Inside the dry-box, a 60 ml bottle equipped with a magnetic stir bar were charged with 0.050 g of tetrabenzylzirconium (0.110 mmol) and 19.1 g of dried, degassed Kaydol oil. The resulting yellow slurry was stirred at ambient temperature for 2 hours, followed by addition of 3.43 g of the above-mentioned SMAO of Example 1. This mixture was then stirred at ambient temperature for 12 hours before being used for polymerization.

Example 3

Preparation of Supported Indene (IN) and Tetrabenzylzirconium (TBZ) mixture of this invention (Composition B)

Inside the dry-box, a 60 ml bottle equipped with a magnetic stir bar were
25 charged with 0.100 g of tetrabenzylzirconium (0.220 mmol), 0.110 g of indene
(0.948 mmol), and 38.0 g of dried, degassed Kaydol oil. The resulting light
orange mixture was stirred at ambient temperature for 2 hours, followed by
addition of 6.70 g of the above-mentioned SMAO of Example 1. The resulting
slurry was then stirred at ambient temperature for 12 hours before being used for
30 polymerization.

Example 4

Treatment of Supported TBZ with Indene of this invention (Composition C)

Inside the dry-box, a silica supported TBZ in Kaydol oil of Example 2 was stirred at ambient temperature while 0.043 g (0.371 mmol) of neat indene was

added. The resulting orange slurry was stirred at ambient temperature for 12 hours before being used for polymerization.

Example 5

Preparation of Supported Pentamethylcyclopentadiene (Cp*) and

5 Tetrabenzylzirconium (TBZ) mixture of this invention (Composition D)

Inside the dry-box, a 60 ml bottle equipped with a magnetic stir bar were charged with 0.049 g of tetrabenzylzirconium (0.108 mmol), 0.061 g of pentamethylcyclopenta-diene (0.449 mmol) and 18.1 g of dried, degassed Kaydol oil. This mixture was stirred at ambient temperature for 2 hours, followed by
10 addition of 3.19 g of the above mentioned SMAO of Example 1. The resulting orange slurry was then stirred at ambient temperature for 12 hours before being used for polymerization.

Example 6

Preparation of Silica Supported Pentamethylcyclopentadiene (Cp*) and

15 Tetrabenzylzirconium (TBZ) mixture of this invention (Composition E)

Same procedure as Example 5 was followed, except 0.028 g of pentamethylcyclopenta-diene (0.206 mmol) was used.

Comparative Example 7

Preparation of Silica Supported Bis(indenyl)zirconium Dichloride (INZ)

Inside the dry-box, a 60 ml bottle equipped with a magnetic stir bar were charged with 0.046 g of INZ and 20.42 g of dried, degassed Kaydol oil. The resulting red slurry was stirred at ambient temperature for 2 hours, followed by
20 addition of 3.0 g of the above mentioned SMAO of Example 1. This mixture was then stirred at ambient temperature for 12 hours before being used for
25 polymerization.

Example 8

Preparation of Bis(pentamethylcyclopentadienyl)zirconium Dipivalate

To a solution of bis(pentamethylcyclopentadienyl)zirconium dichloride (0.865g, 2.001 mmol) and pivalic acid (0.685g, 6.710 mmol) in toluene (30 ml) at
30 40°C was added triethylamine (0.726 g, 7.174 mmol) with stirring. A white precipitate formed immediately which was removed by filtration. The title compound was isolated as an off-white powder in 90% by evaporating the solvent and excess pivalic acid under vacuum at 65°C. The title compound such prepared exhibited purity above 98% based on NMR results. ¹H NMR (toluene d₈) δ1.83
35 (s, 30H), 1.30 (s, 18H).

Comparative Example 9

Preparation of Supported Bis(pentamethylcyclopentadienyl)zirconium Dipivalate

Inside the dry-box, a 60 ml bottle equipped with a magnetic stir bar were
5 charged with 0.062 g of bis(pentamethylcyclopentadienyl)zirconium dipivalate
(0.110 mmol) and 15.0 g of dried, degassed Kaydol oil. This mixture was stirred
at ambient temperature for 2 hours, followed by addition of 2.890 g of the above
mentioned SMAO of Example 1. The resulting slurry was then stirred at ambient
temperature for 12 hours before being used for polymerization.

Polymerization Process

Examples 10 through 16

In each of Examples 10 through 16, polyethylene was produced in a slurry
phase reactor using the catalyst composition specified in Table 1 below.

For each of Examples 10 through 16, a Kaydol oil slurry of one of the
15 catalyst compositions of the invention or comparative examples was prepared. An
aliquot of this slurry mixture was added to a 8 ounce (250 ml) bottle containing
100 ml of hexane. Hexene-1 (20 ml) was then added to the pre-mixed catalyst
composition. Anhydrous conditions were maintained. The polymerization time
for Examples 10 through 6 was 30 minutes.

20 The slurry reactor was a 1 liter, stainless steel autoclave equipped with a
mechanical agitator. The reactor was first dried by heating at 96°C under a stream
of dry nitrogen for 40 minutes. After cooling the reactor to 50°C, 500 ml of
hexane was added to the reactor, followed by 0.25 ml of tri-isobutylaluminum
(TIBA) in hexane (0.86 mole, used as impurity scavenger), and the reactor
25 components were stirred under a gentle flow of nitrogen. The pre-mixed catalyst
composition was then transferred to the reactor under a stream of nitrogen and the
reactor was sealed. The temperature of the reactor was gradually raised to 75°C
and the reactor was pressured to 150 psi (1034 kPa) with ethylene. Heating was
continued until a polymerization temperature of 85°C was attained. Unless
30 otherwise noted, polymerization was continued for 30 minutes, during which time
ethylene was continually added to the reactor to maintain a constant pressure. At
the end of 30 minutes, the reactor was vented and opened.

Table 1 gives the activity, the MI, FI, and MFR of Example 10 through 16.
As shown in Table 1, the catalyst compositions of the invention (Examples 11, 12,

13, and 14) exhibited similar activity to that of the comparative examples.
(Examples 15 and 15)

5

Table 1

Example	Composition used	Zr loading (mmol)	Activity	MI	FI	MFR
10	A	0.001	5714			
11	B	0.001	91726	1.4	25.5	19
12	C	0.001	66496	1.2	22	18
13	D	0.001	14586		0.9	
14	E	0.001	9624		1.4	
15	Comparative Example 7	0.001	74211	1	20	20
16	Comparative Example 9	0.001	14977		2	

While the present invention has been described and illustrated by reference to particular embodiments, those of ordinary skill in the art will appreciate that the invention lends itself to variations not necessarily illustrated herein. For example, it is contemplated that the supported activator, bulky ligand and metal compound may used with one or more bulky ligand metallocene catalysts, or traditional Ziegler-Natta or Phillips-type catalyst. For this reason, then, reference should be made solely to the appended claims for purposes of determining the true scope of the present invention.

CLAIMS

We Claim:

1. A method for preparing a supported catalyst composition comprising the steps of:
 - (a) forming a supported activator; and
 - (b) contacting the supported activator with a bulky ligand and a metal compound.
2. The method of claim 1 wherein the bulky ligand and the metal compound are combined in a liquid prior to contacting with the supported activator.
3. The method of claim 1 wherein the supported activator comprises a support material and an activator.
4. The method of claim 3 wherein the activator is an alumoxane.
5. The method of claim 1 wherein the supported activator is in a mineral oil.
6. The method of claim 2 wherein the liquid is an aliphatic hydrocarbon.
7. The method of claim 1 wherein the metal compound is represented by the formula:
 1. ML_xwherein M is a Group 3 to 12 metal from the Periodic Table of Elements and L is selected from the group consisting of hydrogen, halogen, hydrocarbyl, alkoxide, aryoxide, carboxylate, carbodionate, amide, carbamate and phosphide; and "x" is an integer depending on the valence state of metal.
8. The method of claim 1 wherein the supported activator is the reaction product of a support material comprising surface hydroxyl groups and an organoaluminum compound.
9. The method of claim 1 wherein the metal compound is a Group 4 metal compound.

10. A process for polymerizing olefin(s) in the presence of a supported catalyst system, the supported catalyst system produced by contacting a supported activator, a bulky ligand and a metal compound.
11. The process of claim 10 wherein the process is a gas phase process.
12. The process of claim 10 wherein the supported activator comprises a support material and an activator.
13. The process of claim 10 wherein the metal compound is represented by the formula:

1. ML_x

wherein M is a Group 3 to 12 metal from the Periodic Table of Elements and L is selected from the group consisting of hydrogen, halogen, hydrocarbyl, alkoxide, aryoxide, carboxylate, carbodionate, amide, carbamate and phosphide; and "x" is an integer depending on the valence state of metal.
14. The process of claim 10 wherein the supported catalyst system is in a slurry state.
15. An activated olefin polymerization supported catalyst system comprising a bulky ligand, a metal compound, and supported activator.
16. The supported catalyst system of claim 15 wherein the supported activator comprises a support material and an activator.
17. The supported catalyst system of claim 15 wherein the weight percent of the supported activator to the bulky ligand and metal compound is in the range of from 99.6 to 80.
18. The supported catalyst system of claim 15, wherein the supported activator is a supported alumoxane.

19. The supported catalyst system of claim 15, wherein the activated supported polymerization supported catalyst system is in a liquid.
20. The supported catalyst system 15, wherein the supported activator is in a mineral oil.

ABSTRACT

The present invention relates to a supported catalyst composition and a method for making the supported catalyst composition and its use in a process for polymerizing olefin(s). In particular, the invention is directed to a method for making a supported catalyst composition by contacting a supported activator with a bulky ligand and a metal compound.

"PATENT"**DECLARATION FOR PATENT APPLICATION**

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled

A Method for Preparing a Catalyst System and Its Use in a Polymerization Process

the specification of which is attached hereto unless the following box is checked:

☒ was filed on October 13, 2000 as Application Serial No. or PCT International Application No. _____
and was amended on N/A (if applicable).

I hereby state that I have reviewed and understand the contents of the above identified specification, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the examination of this application in accordance with Title 37, Code of Federal Regulations, § 1.56.

I hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate(s), or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application(s) for patent or inventor's certificate(s), or PCT International application having a filing date before that of the application on which priority is claimed.

<u>Prior Foreign Application(s)</u>			<u>Priority Claimed</u>	
_____ (Number)	_____ (Country)	_____ (Day/Month/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No
_____ (Number)	_____ (Country)	_____ (Day/Month/Year Filed)	<input type="checkbox"/> Yes	<input type="checkbox"/> No

I hereby claim the benefit under 35 U.S.C. § 119(e)(1)-(2) of any United States provisional application(s) listed below.

_____ (Application Number)	_____ (Filing Date)
_____ (Application Number)	_____ (Filing Date)

I hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose material information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

_____ (Application Serial No.)	_____ (Filing Date)	_____ (Status - patented, pending, abandoned)
_____ (Application Serial No.)	_____ (Filing Date)	_____ (Status - patented, pending, abandoned)

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith.

NAMES	REGISTRATION NUMBERS
Jaimes Sher	34,726
Lisa Kimes Jones	41,878
Raul R. Montes	32,545
William G. Muller	32,281

SEND CORRESPONDENCE TO:	DIRECT TELEPHONE CALLS TO: (Name and Telephone Number)
Univation Technologies LLC 5555 San Felipe, Suite 1950 Houston, Texas 77056	Phone No.: (713) 892-3668 Facsimile No.: (713) 892-3687

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

FULL NAME OF INVENTOR	LAST NAME Kao	FIRST NAME Sun-Chueh	MIDDLE NAME
RESIDENCE & CITIZENSHIP	CITY Belle Mead	STATE OR FOREIGN COUNTRY New Jersey	COUNTRY OF CITIZENSHIP United States of America
POST OFFICE ADDRESS	POST OFFICE ADDRESS 7 Durham Court	CITY Belle Mead	STATE OR COUNTRY New Jersey
			ZIP CODE 08502

Inventor's signature _____

Date _____